



PercoTop® 9675

2K HS Topcoat

Features

- PercoTop® 9675 2K HS Topcoat is a high quality, VOC compliant, high solids, 2K topcoat system based on acrylic resin.
- For application on large machinery, cranes, commercial vehicles and industrial constructions.
- Also well-suited to airless or airmix application and with or without electrostatic equipment.

Products

Base Paint

PercoTop® 9675	PercoTop® 9675 2K HS Topcoat
CS975	PercoTop® 2K HS Binder 9675
CS979	PercoTop® 2K HS Matt Binder CV
XXX	Tints

Activators

CS710	PercoTop® Activator VHS Fast
CS711	PercoTop® Activator VHS Standard
CS712	PercoTop® Activator VHS Slow

Thinners

CS610	PercoTop® Thinner Fast
CS620	PercoTop® Thinner Standard
CS630	PercoTop® Thinner Slow

Also possible:

CS640	PercoTop® Thinner Extra Slow
-------	------------------------------

Activators recommended for use with 2K mixing equipment

CS717	PercoTop® Activator HS Extra Slow
CS718	PercoTop® Activator HS Slow
CS719	PercoTop® Activator HS Standard
CS720	PercoTop® Activator HS Fast

Colours

- Fleet, industrial and standard colour registers.





For professional use only!

PercoTop® 9675

2K HS Topcoat

<p>Substrates</p> <ul style="list-style-type: none"> • Primed surfaces. • Cured, solvent resistant, well preserved and scuff sanded old finish.

Surface preparation



Substrates must be free from all contaminants.	
Apply to	PercoTop® Primer/Primer Surfacer or old paintwork.
	Thoroughly clean old paintwork.
Either	 Sand dry with orbital sander and dust exhaust P320-P500.
or	 Sand wet with sandpaper P600-P800.
	Before further treatment, carefully clean sanded areas once more to remove all dust, paint residues from sanding and other impurities.

PercoTop® 9675

2K HS Topcoat

VOC value ready for use (EU Directive 1999/13/EC)	
• < 420 g/l	3:1 by volume with CS710 + 15% CS610.







Product preparation

 Mixing ratio	PercoTop® 9675 CS710/CS711/CS712 CS717/CS718/CS719/CS720	Standard		Matt
		Volume		Volume
		3	2	5
		1	1	1
Thinner	CS610 CS620 CS630 CS640 <u>Remarks:</u> - Use CS610 on small objects at 15-25°C. - Use CS620 on medium sized objects at 20-25°C. - Use CS630 on large objects at 20-30°C. - Use CS640 on large objects when exceeding 30°C.			
 Pot life at 20°C	2-3 hours (depending on hardener used)			

PercoTop[®] 9675

2K HS Topcoat

Application

	Application viscosity DIN 4 mm at 20°C (s)	Thinner (%)	Spray nozzle (mm)	Pressure (bar)	Number of coats
 Gravity feed  Suction feed (High pressure spraying)	22-26	HS: 0-5 VHS: 10-15	1.4-1.6	2.5-3.5	1.5
 HVLP (Low pressure spraying)	22-26	HS: 0-5 VHS: 10-15	1.4-1.6	2.0-2.5	1.5
 Airless Airmix	30-35	HS: as mixed VHS: 5	0.23-0.28	2.0-3.0 air ca. 80-100 material	1
 Pressure pot Membrane pump (High pressure spraying)	22-26	HS: 0-5 VHS: 10-15	1.1	2.5-3.5 air 1.0-2.0 material	1.5
 Electrostatic	According to the advice of the Technical Representative.				
Recommended dry film thickness	50-80 µm				

PercoTop[®] 9675

2K HS Topcoat



Drying

Air drying at 20°C	70 µm dry film thickness
Dust dry	20 minutes - 1 hour
Dry to handle	4-6 hours
Dry to assemble	16 hours
Forced drying	Flash time: 15 minutes. Depending on film thickness.
Drying time	30 minutes
Drying temperature	60°C object temperature

Product data

	Solids Weight (%) +/- 1	Density (kg/l) +/- 0.01	Theoretical coverage (at 50 µm) (m ² /kg)	Theoretical material consumption (at 50 µm) (g/m ²)
White				
Packaged	72	1.31	-	-
Ready for use	66	1.21	11	92
Black				
Packaged	61	0.99	-	-
Ready for use	58	1.00	12	88

Remarks

	<ul style="list-style-type: none"> Stir well before use.
	<ul style="list-style-type: none"> Axalta recommends the customer should perform a quick colour-check of products before use.
Storage Conditions	<ul style="list-style-type: none"> Refer to the label on the original can.

<p>Safety</p> <p>Consult the Safety Data Sheet prior to use. Observe the precautionary notices displayed on the container.</p>



PercoTop[®] 9675

2K HS Topcoat

Information

The information provided herein corresponds to our knowledge on the subject at the date of its publication. This information may be subject to revision as new knowledge and experience becomes available. The data provided fall within the normal range of product properties and relate only to the specific material designated; these data may not be valid for such material used in combination with any other materials or additives or in any process, unless expressly indicated otherwise. The data provided should not be used to establish specification limits or used alone as the basis of design; they are not intended to substitute for any testing you may need to conduct to determine for yourself the suitability of a specific material for your particular purposes. Since Axalta cannot anticipate all variations in actual end-use conditions Axalta makes no warranties and assumes no liability in connection with any use of this information. Nothing in this publication is to be considered as a license to operate under or a recommendation to infringe any patent rights.

This Technical Data Sheet supersedes all previous issues.

Copyright © 2014, Axalta Coating Systems, LLC and all affiliates. All rights reserved. The Axalta logo, Axalta™, Axalta Coating Systems™ and all products denoted with ™ or ® are trademarks or registered trademarks of Axalta Coating Systems, LLC and its affiliates. Axalta trademarks may not be used in connection with any product or service that is not an Axalta product or service.